



MINIMUM STANDARDS

ITEM	DESCRIPTION	THROUGHFARE	COMM. & IND.	COLLECTOR	LOCAL	RESIDENTIAL	LOCAL/RESIDENTIAL NO. PARKING
I	RIGHT-OF-WAY	*	60	60	50	60	45
II	B\B CURB	*	41	36	30	36	24
III	SIDEWALK WIDTH	*	5'	5'	5'	5'	5'
IV	CURB LAWN WIDTH	*	4.5'	7'	4'	4'	4'
V	ITEM 448	1-1/4"	1-1/4"	1-1/4"	1-1/4"	1-1/4"	1-1/4"
VI	ITEM 448	1-3/4"	1-3/4"	2-3/4"	2-1/4"	2-3/4"	2-3/4"
VII	ITEM 301	7"	3"	—	—	—	—
VIII	ITEM 304	6"	9"	9"	9"	9"	9"
V	ITEM 448	1-1/4"	1"	1"	1"	1"	1"
VI	ITEM 448	1-3/4"	2"	2"	2"	2"	2"
VII	ITEM 301	8"	6"	5"	4"	5"	5"
VIII	ITEM 301	2 LIFTS	2 LIFTS	2 LIFTS	2 LIFTS	2 LIFTS	2 LIFTS

* SEE DESIGN CRITERIA AND CITY ENGINEER

NOTES

- A. ALL WORK TO CONFORM TO ODOT CONSTRUCTION AND MATERIAL SPECIFICATIONS LATEST REVISION UNLESS OTHERWISE SPECIFIED.
- B. ITEM 407 TACK COAT, SHALL BE REQUIRED WHEN 5 DAYS HAVE ELAPSED BETWEEN BITUMINOUS PAVEMENT LIFTS UNLESS OTHERWISE SPECIFIED BY THE ENGINEER. APPLICATION RATE IS 0.10 GALLON PER SQUARE YARD.
- C. ALL BUTT JOINTS SHALL BE SEALED WITH PG 64-22 WITHIN 24 HOURS AFTER PLACEMENT OF ITEM 448.
- D. STANDARD DIMENSIONS FOR (II) B\B CURB AND (IV) APRON WIDTH ASSUME PARKING ON BOTH SIDES.
- E. SIDEWALK OF 4' WIDTH MAY BE APPROVED BY THE CITY ON ARTERIAL, AND COMMERCIAL. SIDEWALKS ARE NOT REQUIRED ON INDUSTRIAL STREETS.
- F. IN AREAS WITH HIGH POTENTIAL OF PUSHING, SHOWING OR HEAVING, USE ITEM 448 ASPHALT CONCRETE SURFACE COURSE TYPE 1 H, PG. 70-22, IN SMALL QUANTITY AREAS USE TYPE 1, PG. 64-22 WITH GILSONITE ADDITIVE.
- G. CONCRETE PAVEMENT WILL BE CONSIDERED UPON SUBMITTAL OF TYPICAL SECTION DESIGN.



CITY OF
SIDNEY

**TYPICAL SECTIONS AND
ASPHALT PAVEMENT COMPOSITION**

REVISIONS:
06-25-07
07-22-13

DATE
APPROVED:
FEB. 2002
PAGE No.
300-2